



FOAMULAR® Extruded Polystyrene (XPS) Insulation ASTM C578—Types and Physical Properties

Technical Bulletin

This table outlines the basic physical property requirements of ASTM C578¹ and FOAMULAR® XPS insulation compliance. The products are organized, left to right, in ascending compressive strength. For complete details on board types, properties and other quality requirements see the actual ASTM standard.

Polystyrene Board Type ²	EPS	EPS	EPS	FOAMULAR® 150, XPS	EPS	FOAMULAR® 250, XPS	EPS	FOAMULAR® 400, XPS	EPS	FOAMULAR® 600, XPS	EPS	FOAMULAR® 1000, XPS
ASTM C578 Classification	Type XI	Type I	Type VIII	Type X	Type II	Type IV	Type IX	Type VI	Type XIV	Type VII	Type XV	Type V
Compressive resistance at yield or 10 % deformation, whichever occurs first (with skins intact) min, psi (kPa)	5.0 (35)	10.0 (69)	13.0 (90)	15.0 (104)	15.0 (104)	25.0 (173)	25.0 (173)	40.0 (276)	40.0 (276)	60.0 (414)	60.0 (414)	100.0 (690)
Density, min, lb/ft ³ (kg/m ³)	0.70 (12)	0.90 (15)	1.15 (18)	1.30 (21)	1.35 (22)	1.55 (25)	1.80 (29)	1.80 (29)	2.40 (38)	2.20 (35)	2.85 (46)	3.00 (48)
Thermal resistance of 1.00-in. (25.4-mm) thickness, min, hr•ft ² •°F/Btu (K•m ² /W) Mean temperature: 75 2° (24 1°C)	3.10 (0.55)	3.60 (0.63)	3.80 (0.67)	5.00 (0.88)	4.00 (0.70)	5.00 (0.88)	4.20 (0.74)	5.00 (0.88)	4.20 (0.74)	5.00 (0.88)	4.30 (0.76)	5.00 (0.88)
Flexural strength, min, psi (kPa)	10.0 (70)	25.0 (173)	30.0 (208)	40.0 (276)	35.0 (240)	50.0 (345)	50.0 (345)	60.0 (414)	60.0 (414)	75.0 (517)	75.0 (517)	100.0 (690)
Water vapor permeance of 1.00-in. (25.4-mm) thickness, max, perm (ng/Pa•s•m ²)	5.0 (287)	5.0 (287)	3.5 (201)	1.5 (86)	3.5 (201)	1.5 (86)	2.5 (143)	1.1 (63)	2.5 (143)	1.1 (63)	2.5 (143)	1.1 (63)
Water absorption by total immersion, max, volume	4.0	4.0	3.0	0.3	3.0	0.3	2.0	0.3	2.0	0.3	2.0	0.3

1. ASTM C578-10, "Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation"; published by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959

2. XPS is extruded polystyrene. EPS is expanded polystyrene, also known as molded polystyrene.

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.



OWENS CORNING FOAM INSULATION, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659

1-800-GET-PINK®
www.owenscorning.com

Pub. No. 10015702. Printed in U.S.A. September 2011. THE PINK PANTHER™&©1964-2011 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. ©2011 Owens Corning.

