



Product Data Sheet



Physical Property Data

Property	Value
Weight Range (GSM)	150 - 600
Thickness Range (mm)	1.6 - 3.5
Color	White
k-value @ 8.4 PCF density (ambient temperature)	.25
Flammability	
UL94 5VA	Pass
UL94 V-0	Pass
UL94 HB	Pass
FMVSS 302	Pass

- High thermal stability
- No chemical binders
- Ease of handling
- Thin, pliable product spectrum
- Design flexibility
- Excellent conformability

Product Applications

Owens Corning™ PliaTemp™ 1000 Series Insulation's extensive range of properties make it an excellent material option for a broad spectrum of applications.

PliaTemp™ 1000 insulation can be laminated with various facings, die cut or processed in numerous other methods to ensure its performance meets customer specific criteria.

PliaTemp™ 1000 insulation is great for any limited space application requiring an insulating material with exceptional heat resistant properties. PliaTemp™

1000 can be designed to match customer fitness for use criteria in application locations restricted to spaces as thin as 1/16" (1.6mm).

We can engineer a solution to your new insulation problems, or work with you to provide an effective alternative to your current insulation products. Please contact your Area Sales Representative for a consultation and more information on this exciting product, as well as other insulating solutions that can improve your product offering.

Availability

Owens Corning™ PliaTemp™ Insulation is available in rolls of varying weights, thicknesses, width and lengths. Consult your Area Sales Representative for a more information concerning your specific requirements.

Description

Owens Corning™ PliaTemp™ 1000 Series Insulation is an advanced thermal insulation engineered to provide excellent heat and flame resistance. The proprietary composition of PliaTemp™ 1000 fiber blends have a high Limiting Oxygen Index (LOI) and are specifically designed to meet particular thermal and structural requirements.

Key Features

Owens Corning™ PliaTemp™ 1000 Series unique construction offers an extensive property profile which includes:

- Excellent heat resistance
- Passes UL94 5VA (the highest, most flame retardant UL rating)

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.



OWENS CORNING INSULATING SYSTEMS, LLC
 ONE OWENS CORNING PARKWAY
 TOLEDO, OHIO, USA 43659
1-800-GET-PINK®
www.owenscorning.com

Pub. No. 10019210. Printed in U.S.A. July 2014. THE PINK PANTHER™ & ©1964-2014 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. ©2014 Owens Corning. All Rights Reserved.

